



RAPTOR 1K TRUCK BED COATING GRAY AEROSOL

UP4878



DRIVING SURFACE PERFECTION Version: 2.0 Date of issue: 17/07/2020 Revision date: 31/03/2021 Supersedes: 17/07/2020

TECHNICAL DATASHEET

RAPTOR Truck Bed Coating is ideal for protecting truck beds and other vehicle surfaces from impact, scratches, corrosion and water damage. Its 1K formulation gives a durable, abrasion resistant finish with excellent adhesion to metal, aluminum, fiberglass, plastic and wood. Clog free and easy to use, it dries to form an attractive, textured finish that resists fading from the sun.

- Textured finish.
- Durable, impact & abrasion resistant 1K coating.
- Ideal for truck beds, tail gates, running boards, fender flares and more.

Product	Order Code	Format	Shelf Life
RAPTOR 1K TRUCK BED COATING GRAY AEROSOL	UP4878	486ml Aerosol	5 years

APPLICATION INFORMATION



FOR PPE RECOMMENDATIONS REFER TO SDS

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the safety data sheet for full handling instructions and personal protection information.



Surface Preparation



Substrate	Degreaser	Abrasion
Bare Steel*	SYSTEM 20 Solvent-Based Degreaser	P80 - P120
Aluminum*	SYSTEM 20 Solvent-Based Degreaser	P120
Galvanised*	SYSTEM 20 Solvent-Based Degreaser	P120
Prepared OEM surfaces	SYSTEM 20 Solvent-Based Degreaser	P80 - P120
SMC, Fiberglass	SYSTEM 20 Water-Based Degreaser	P80 - P120
Lightly abraded E-Coat	SYSTEM 20 Solvent-Based Degreaser	Not required
Most Plastics**	SYSTEM 20 Water-Based Degreaser	P120
Wood	Not required	Not required

For best results, good preparation is essential. Clean and degrease removing dirt, oil, grease and wax with cleaning solutions such as U-POL's SYSTEM 20 Degreasers (please check local VOC regulations). Abrade with grit paper as stated above for each respective substrate. Re-clean, dry and degrease the abraded substrate ready for application. *For optimum results, apply 1-2 light even coats of RAPTOR Acid Etch Primer, allowing 20 minutes drying time before application. **Plastics should be treated with an adhesion promoter such as RAPTOR Adhesion Promoter Aerosol. PLEASE NOTE: this product is not recommended for application over thermoplastic acrylics.

Mixing



Shake the aerosol can for at least 2 minutes before use.

Application



Application Temperature	20 °C / 70 °F
Distance from the surface	30 cm / 12 inches
Number of Coats	1 – 2
Flash-off at 70°F	10 – 15 minutes between coats
Total Dry Film Thickness	140 µm / 5.5 MIL
Theoretical Coverage @ indicated DFT*	0.8 m ² /unit / 8.4 ft ² /unit
	*Theoretical Coverage assuming total dry film thickness is attained at 100% transfer efficiency.

Drying Time



PLEASE NOTE: drying times are dependent upon film thickness, humidity and temperature.

Touch Dry at 70°F	< 60 minutes
Dry-Through at 70°F	3 – 4 hours

Overcoating



This formulation can be directly overcoated without sanding with most water/solvent-based paint systems.

Overcoatable at 70°F after	3 – 4 hours
-----------------------------------	-------------

TECHNICAL INFORMATION

Physical properties



Appearance	Aerosol.
Color	Gray
Density	0.855 kg/m ³





RAPTOR 1K TRUCK BED COATING GRAY AEROSOL

UP4878



DRIVING SURFACE PERFECTION Version: 2.0 Date of issue: 17/07/2020 Revision date: 31/03/2021 Supersedes: 17/07/2020

TECHNICAL DATASHEET

	<p>Maximum Incremental Reactivity (MIR) 0.67 MIR EPA Aerosol Category FCP 1.2 - Flat Coating MIR CARB Aerosol Category FCP 0.80 - Flat Coating - General Coatings</p> <p>As Packaged Regulatory VOC 527 g/l (4.4 lbs/gal) As Packaged Actual VOC 479 g/l (4.0 lbs/gal) As Applied Regulatory VOC 527 g/l (4.4 lbs/gal) As Applied Actual VOC 479 g/l (4.0 lbs/gal) Percent Solids 34.02 wt% Percent Solids 22.43 vol % Volatiles 66.0 wt% Water Content 0 wt% Water Content 0 vol % Exempt Compounds by weight 10 wt% Exempt Compounds by volume 9.2 vol % % EPA HAPS 4.1 wt%</p>																					
<p>Storage</p> 	<p>Aerosol cans should be stored for two hours at room temperature before use. For long term storage, keep in a dry well ventilated area and away from direct sunlight and frost. To clear the nozzle and maximise the lifespan of your aerosol, always invert the can and spray upside down for a few seconds after each use. Should the nozzle become blocked, remove it from the can and soak it in gentle thinners.</p> <p>Protect from sunlight. Store in a well-ventilated place. Do not expose to temperatures exceeding 50 °C/ 122 °F. Store locked up. Keep container tightly closed. Keep cool.</p> <p>Recommended storage temperature 40 °C - 75 °F</p>																					
<p>Associated Products</p> 	<table border="1"> <thead> <tr> <th>Product</th> <th>Order Code</th> <th>Format</th> </tr> </thead> <tbody> <tr> <td>SYSTEM 20 Water-Based Degreaser</td> <td>UP2002</td> <td>5L Canister</td> </tr> <tr> <td>SYSTEM 20 Solvent-Based Fast Degreaser</td> <td>UP2012</td> <td>5L Tin</td> </tr> <tr> <td>SYSTEM 20 Solvent-Based Slow Degreaser</td> <td>UP2022</td> <td>5L Tin</td> </tr> <tr> <td>WIPE #6 Solvent-Based Degreaser Aerosol</td> <td>UP0872</td> <td>450ml Aerosol</td> </tr> <tr> <td>RAPTOR Acid Etch Primer Aerosol</td> <td>UP5023</td> <td>450ml Aerosol</td> </tr> <tr> <td>RAPTOR Adhesion Promoter Aerosol</td> <td>UP5024</td> <td>450ml Aerosol</td> </tr> </tbody> </table>	Product	Order Code	Format	SYSTEM 20 Water-Based Degreaser	UP2002	5L Canister	SYSTEM 20 Solvent-Based Fast Degreaser	UP2012	5L Tin	SYSTEM 20 Solvent-Based Slow Degreaser	UP2022	5L Tin	WIPE #6 Solvent-Based Degreaser Aerosol	UP0872	450ml Aerosol	RAPTOR Acid Etch Primer Aerosol	UP5023	450ml Aerosol	RAPTOR Adhesion Promoter Aerosol	UP5024	450ml Aerosol
Product	Order Code	Format																				
SYSTEM 20 Water-Based Degreaser	UP2002	5L Canister																				
SYSTEM 20 Solvent-Based Fast Degreaser	UP2012	5L Tin																				
SYSTEM 20 Solvent-Based Slow Degreaser	UP2022	5L Tin																				
WIPE #6 Solvent-Based Degreaser Aerosol	UP0872	450ml Aerosol																				
RAPTOR Acid Etch Primer Aerosol	UP5023	450ml Aerosol																				
RAPTOR Adhesion Promoter Aerosol	UP5024	450ml Aerosol																				

U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the information is up to date. The recommendation of use of our products and application in our technical data sheets are based on our knowledge and experience. These data sheets are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits. U-POL is not liable for mis-use or abuse of its products and no application warranty is expressed or implied.

For additional technical assistance, please contact the U-POL Technical Department at technicalsupport@u-pol.com

U-POL US Inc
108 Commerce Way
Easton, PA 18040 - United States
T 1-800-340-7824 - F 1-800-787-5150
technicalsupport@u-pol.com - www.u-pol.com